



Sun Control Textiles™

## WELDING TAPE T00122 DATA SHEET

<b>Description:</b>	Thermoplastic Adhesive Film T00122
<b>Size:</b>	10mm (1/32") x 50 linear meters (55 yards)
<b>Composition:</b>	Co-Polyester
<b>Color:</b>	Slightly Opaque
<b>Density:</b>	1.24 g/cm <sup>3</sup>
<b>Washability:</b>	Excellent up to 60°C / 140°F
<b>Softening Point:</b>	110-130°C / 230-266°F
<b>Melt Flow Index (MFI):</b>	30-60 g/10 min.
<b>Heat Resistance:</b>	90°C / 195°F

### Recommended Applications<sup>1</sup>:

Recommended for polyester fabrics and acrylic backed, polyester blackout fabrics

Can be processed with all established calendaring, lamination, and bonding techniques such as high frequency and impulse welding

<sup>1</sup>Recommended conditions will vary between different machinery and fabrics. The recommended conditions stated are a starting point only. Optimal bonding conditions should be established by the factory for the specific application.