

## Elba Twilight™

### Specifications

<b>Product Category:</b>	Privacy	<b>Composition:</b>	100% polyester with acrylic coating
<b>Openness Factor:</b>	0%	<b>Standard Packaging:</b>	Rolls of 33 ly (30 lm)
<b>UV Blockage:</b>	Approximately 100%	<b>Width:</b>	118" (300 cm)
<b>Fabric Style:</b>	Blackout	<b>Weight:</b>	11.8 oz / yd2 (400 g / m2) ± 10%
<b>Item #:</b>	022400	<b>Thickness:</b>	0.027" (0.68 mm) ± 10%

### Fenestration Data

			Fabric Properties						Fabric & Glass	Illuminance	
			Thermal				Optical				
Color #	Color Name	Side*	Rs IR (%)	Total Solar			Rv (%)	Tv (%)	SHGC	Blackout %	Glow %
				Rs (%)	As (%)	Ts (%)					
000QUA	Quartz	street	76	80	20	0	88	0	0.19	98	2
		room	70	75	25	0	80	0	0.22	98	2
000PMC	Pumice	street	81	82	18	0	89	0	0.18	98	2
		room	76	73	27	0	73	0	0.24	98	2
000LIM	Limestone	street	80	84	16	0	91	0	0.17	99	1
		room	70	68	32	0	68	0	0.27	99	1
000SLA	Slate	street	76	80	20	0	87	0	0.19	99	1
		room	76	64	36	0	56	0	0.30	99	1
000BAS	Basalt	street	62	68	32	0	77	0	0.26	98	2
		room	65	52	48	0	42	0	0.36	98	2
000OBS	Obsidian	street	81	82	18	0	87	0	0.18	99	1
		room	35	24	76	0	14	0	0.50	99	1

\*Room side: identified by the fabric side; Street side: identified by the coated side

Fabric properties may vary from the values reported due to standard variations in the manufacturing process. The fabric fenestration testing was conducted in accordance with ASTM G173 & ASTM E903: Total Solar Transmittance (Ts), Total Solar Reflectance (Rs), Solar Reflectance in Infrared (Rs IR), Total Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory WINDOW NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / 1/2" air / 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass / 1/2" air / 3mm clear glass. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423: NRC is Noise Reduction Coefficient; SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact Mermet at [info@MermetUSA.com](mailto:info@MermetUSA.com).

#### Fabrication Methods:

**Cutting:** Crush, cold, or ultrasonic

**Welding:** Mermet T00119 Tape is Recommended.

300-350°F. 15s.

Radio frequency, impulse, hot air, wedge

#### Fire Classifications:

ASTM E 84 (Class B)

California Technical Bulletin #117

#### Bacterial Resistance:

ASTM E2180

#### Environmental Benefits:

RoHS - Lead Free

GREENGUARD Gold

#### Acoustical Performance:

NRC: 0.00, SAA: 0.03

We recommend testing all cutting and welding methods or settings with your equipment to confirm they meet your individual fabrication specifications.

#### Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains. Handling: Support the full width of the roll to prevent uneven distribution of weight and fabric deformation.

5970 N. Main Street • Cowpens, SC 29330

Sales Department: Ph (866) 902-9647

[info@MermetUSA.com](mailto:info@MermetUSA.com)

