

## Specifications

Product Category	/: Privacy	Composition:	100% polyester with acrylic coating	ng <u>White Backing</u>		
<b>Openness Factor</b>	: 0%	Roll Length:	Standard Rolls of 33 ly (30 lm)	Weight:	12.8 oz / yd2 (433 g / m2) ± 10%	
UV Blockage:	Approximately 100%	Width:	126" (320 cm)	Thickness	: 0.021" (0.53 mm) ± 10%	
Fabric Style:	Blackout			Color Mat	ched Backing	
Item #:	022100			Weight:	11.0 oz / yd2 (374 g / m2) ± 10%	
				Thickness	: 0.017" (0.44 mm) ± 10%	

## **Fenestration Data**

			Fabric Properties					Fabric & Glass	Illuminance		
			Thermal Optical					Fabric & Glass			
Color #	Color Name	Side*	Rs IR (%)	Total Solar		Dv (9/)	T. (0/)	SHGC	Blackout %	Glow %	
COIOF #	Color Name		KS IK (%)	Rs (%)	As (%)	Ts (%)	Rv (%)	Tv (%)	SHGC	BIACKOUT %	GIUW %
002002	White/White	street	65	70	30	0	77	0	0.25	100	0
		room	80	84	16	0	92	0	0.16	100	0
016002	Chalk/White	street	66	70	30	0	77	0	0.25	100	0
		room	61	63	37	0	67	0	0.29	100	0
012002	Frost/White	street	70	73	27	0	79	0	0.23	100	0
		room	50	53	47	0	58	0	0.35	100	0
017002	Canvas/White	street	70	73	27	0	79	0	0.23	100	0
		room	67	68	32	0	72	0	0.27	100	0
020002	Linen/White	street	70	73	27	0	79	0	0.23	100	0
		room	53	52	48	0	54	0	0.35	100	0
015002	Khaki/White	street	65	70	30	0	77	0	0.25	100	0
		room	36	38	62	0	41	0	0.43	100	0
001002	Pewter/White	street	67	70	30	0	77	0	0.25	100	0
		room	15	18	82	0	20	0	0.52	100	0
050002	Graphite/White	street	64	69	31	0	76	0	0.25	100	0
		room	8	8	92	0	9	0	0.56	100	0
060002	Black/White	street	71	74	26	0	80	0	0.23	100	0
		room	3	3	97	0	3	0	0.58	100	0
001001	Pewter/Pewter	street	16	17	83	0	17	0	0.53	100	0
		room	15	18	82	0	20	0	0.52	100	0
050050	Graphite/Graphite	street	7	7	93	0	7	0	0.57	100	0
		room	7	8	92	0	9	0	0.56	100	0
060060	Black/Black	street	5	6	94	0	6	0	0.57	100	0
		room	3	3	97	0	3	0	0.58	100	0

\*Room side: identified by the fabric side; Street side: identified by the coated side

Fabric properties may vary from the values reported due to standard variations in the manufacturing process. The fabric fenestration testing was conducted in accordance with ASTM G173 & ASTM E903: Total Solar Transmittance (Ts), Total Solar Reflectance (Re), Solar Reflectance (Re), Reflectance (Re), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHCQ) were conducted using the Lawrence Berkeley National Laboratory WINDOW NFRC certified Software. SHCG 's improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / ½" air / 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass / 12" air / 3mm clear glass. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423: NRC is Noise Reduction Coefficient; SAA is Sound Absorption Average. For up-to-date test results, performance and larger samples; contact MermetUSA.com.

## Fabrication Methods:

Cutting: Crush, cold, or ultrasonic Welding: Mermet 103218 Tape is Recommended. 350°F. 15s. Radio frequency, impulse, hot air, wedge Fire Classifications: ASTM E 84 (Class B) California Technical Bulletin #117 Bacterial Resistance: ASTM E2180 Environmental Benefits: RoHS - Lead Free GREENGUARD Gold

We recommend testing all cutting and welding methods or settings with your equipment to confirm they meet your individual fabrication specifications.

## Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains. Handling: Support the full width of the roll to prevent uneven distribution of weight and fabric deformation.

5970 N. Main Street • Cowpens, SC 29330 Sales Department: Ph (866) 902-9647 info@MermetUSA.com

